

Product Data Sheet www.RichardsApex.com

AC150 COMPOUND

RichardsApex AC150 is especially formulated to provide protection against oxidation on hot rolled and Concast aluminum rod in shipping and storage. In addition to its protective coating properties, AC150 also deposits a lubricating film that will be advantageous in subsequent packaging, pay off, and drawing operations.

Benefits

Provides excellent lubrication for coiling Concast rod

Protects surface finish during storage and shipping

Easy to handle liquid form

Coating aids subsequent dry drawing operations

Dry film does not pick up mill dirt

Recommended Uses

Apply by coil dipping, stand immersion, or direct spray.

Concentration – 10% by volume.

Operating Temperature – 60°C (140°F)

Specifications

Density	1.02 kg/L	8.5 lbs/gal
pH of a 3% DI solution	8.8	